

A Review on Effect of Pozzolanas on Fibre Reinforced Concrete

Mohammad Mustafa ^{#1}, Honey Gaur ^{*2}

^{#1}Research scholar, Department of Civil Engineering, Kalinga University, Raipur

^{*2}Asst. Professor, Department of Civil Engineering, Kalinga University, Raipur

Abstract

Strength was emphasized without a thought on the durability of structures. As a consequence of the liberties taken, the durability of concrete and concrete structures is on a southward journey; a journey that seems to have gained momentum on its path to self-destruction.

Keyword-Strength, concrete.FRC

INTRODUCTION

In recent years, the terminology "High-Performance Concrete" has been introduced into the construction industry. The American Concrete Institute (ACI) defines high-performance concrete as concrete meeting special combinations of performance and uniformity requirements that cannot always be achieved routinely when using conventional constituents and normal mixing, placing and curing practices. A commentary to the definition states that a high-performance concrete is one in which certain characteristics are developed for a particular application and environment.

LITERATURE REVIEW

Aitcin (1995) cited on development in the application of high performance concrete. Over the last few years, the compressive strength of some of the concrete used has increased dramatically. In 1988, a 120 MPa concrete was delivered on site, while, until relatively recently, 40 MPa was considered indicative of high strength. The spectacular increase in compressive strength is directly related to a number of recent technological developments, in particular the discovery of the extraordinary dispersing action of superplasticizers with which flowing concretes can be made with about the same mixing water that is actually required to hydrate all the cement particles or even less. The reduction in water/cement ratio results in a hydrated cement paste with a microstructure so dense and strong that coarse aggregate can become the concrete's weakest constituent. Silica fume, a highly reactive pozzolana, considerably enhances the paste/aggregate interface and minimizes debonding. Lastly, the use of supplementary cementitious materials, such as fly ash and especially slag, helps solve slump loss problems which become critical at low w/c ratios.

Ajdukiewicz and Radomski (2002) delve into Trends in the Polish research on high-performance concrete. They analysed the main trends in the research on high-performance concrete (HPC) in Poland. There they sighted on some examples of the relevant investigations. The fundamental engineering and economic problems concerning the structural applications of HPC in Poland are presented as well as the needs justifying the increased use of this material are briefly described.

Aitcin (2003) studied on the durability characteristics of high performance concrete. He examined durability problems of ordinary concrete can be associated with the severity of the environment and the use of inappropriate high water/binder ratios. High-performance concrete that have a water/binder ratio between 0.30 and 0.40 are usually more durable than ordinary concrete not only because they are less porous, but also because their capillary and pore networks are somewhat disconnected due to the development of self-desiccation. In high-performance concrete (HPC), the penetration of aggressive agents is quite difficult and only superficial. However, self-desiccation can be very harmful if it is not controlled during the early phase of the development of hydration reaction, therefore, HPC must be cured quite differently from ordinary concrete. Field experience in the North Sea and in Canada has shown that HPCs, when they are properly designed and cured, perform satisfactorily in very

harsh environments. However, the fire resistance of HPC is not as good as that of ordinary concrete but not as bad as is sometimes written in a few pessimistic reports. Concrete, whatever its type, remains a safe material, from a fire resistance point of view, when compared to other building materials.

Al-Khalaf and A. Yousif (1984) examined on use of RHA in concrete. They studied the actual range of temperature require to burn rice husk in order to get the desired pozzolanic product, use of rice husk as partial replacement of cement on compressive strength and volume changes of different mixes. And showed that up to 40% replacement can be made with no significant change in compressive strength compared with the control mix. He tested on mortar cube, by testing on 50 mm cubes. In his investigation alsohe deduced that the most convenient and economical burning conditions required to convert rice husks into a homogenous and well burnt ash is at 500⁰ C for 2 hours. Also for a given grinding time, there is a considerable reduction in the specific surface area of RHA as burning temperature increases. For mortar mix with constant RHA content, the water requirement decreases as the fineness of the ash increases. The minimum pozzolanic activity can be obtained, when the ash has a specific surface of about 11,500 cm²/gm. The strength of cement-RHA mortar approaches the strength of the corresponding plain mortar when the specific surface of RHA about 17000cm²/gm. For 1:2 and 1:3 mortar mixes of standard consistency the maximum percentage of rice husk ash that can be replaced by weight of cement without 60 days strength being less than that of plain mortar was 30% and 40 % respectively. Also he found higher the percentage or RHA, higher is the volume change characteristic corresponding to plain mortar.

Ismail and waliuddin (1996) had worked on effect of rice husk ash on high strength concrete. They studied the effect of rice husk ash (RHA) passing 200 and 325 micron sieves with 10-30% replacement of cement on the strength of HSC. The RHA was obtained by burning rice husk, an agro-waste material which is abundantly available in the developing countries. A total of 200 test specimens casted and tested at 3,7,28 and 150 days. Compressive and split tensile strengths of the test specimens.Cube strength over 70 MPa was obtained without any replacement of cement by RHA. Test results indicated that strength of HSC decreased when cement was partially replaced by RHA for maintaining same level of workability. They observed that optimum replacement of cement by RHA was 10-20%, and even from crystalline form of RHA good result may be obtained by fine grinding.

De Sensale (2006) studied on strength development of concrete using rice husk ash. This paper presents a study on the development of compressive strength up to 91 days of concretes with rice-husk ash (RHA), in which residual RHA from a rice paddy milling industry in Uruguay and RHA produced by controlled incineration from the USA were used for comparison. Two different replacement percentages of cement by RHA, 10% and 20%, and three different water/cementitious material ratios (0.50, 0.40 and 0.32), were used. The results are compared with those of the concrete without RHA, with splitting tensile strength and air permeability. It is concluded that residual RHA provides a positive effect on the compressive strength at early ages, but the long term behavior of the concretes with RHA produced by controlled incineration was more significant. Results of splitting tensile and air permeability reveal the significance of the filler and pozzolanic effect for the concretes with residual RHA and RHA produced by controlled incineration.

Oner A and Akyuz S (2007) studied on optimum level of ground granulated blast furnace slag (GGBS) on compressive strength of concrete. In their study GGBS was added according to the partial replacement method in all mixtures. A total of 32 mixtures were prepared in four groups according to their binder content. Eight mixes were prepared as control mixtures with 175, 210, 245 and 280 kg/m³ cement content in order to calculate the Bolomey and Feret coefficients (KB, KF). For each group 175, 210, 245 and 280 kg/m³ dosages were determined as initial dosages, which were obtained by removing 30 percent of the cement content of control concretes with 250, 300, 350, and 400 kg/m³ dosages. Test concretes were obtained by adding GGBS to concretes in an amount equivalent to approximately 0%, 15%, 30%, 50%, 70%, 90% and 110% of cement contents of control concretes with 250, 300, 350 and 400 kg/m³ dosages. All specimens were moist cured for 7, 14, 28, 63, 119, 180 and 365 days before compressive strength testing. The test results proved that the compressive strength of concrete mixtures containing GGBS increases as the amount of GGBS increase. After an optimum point, at around 55% of the total binder content, the addition of GGBS does not improve the compressive strength. This can be explained by the presence of unreacted GGBS, acting as a filler material in the paste.

It was found that as the GGBS content increases, the water-to-binder ratio decreases for the same workability. The early strength of GGBS concrete was lower than that of the control concrete. However, as the curing period is extended the strength increase was higer for GGBS concrete.The compressive strength of GGBS concrete increases as the GGBS content is increased up to an optimum point, after which the compressive strength decreases. The optimum level of GGBS content for maximizing strength is at about 55–59% of the total binder content.

Qian Jueshi and Shi Caijun (2000) studied on high performance cementing materials from industrial slag. They found most industrial slags are being used without taking full advantage of their properties or disposed rather than used. The industrial slags, which have cementitious or pozzolanic properties, should be used as partial or full replacement for Portland cement rather than as bulk aggregates or ballasts because of the high cost of Portland cement, which is attributable to the high energy consumption for the production of Portland cement. The traditional way to utilize metallurgical slags in cementing materials is to partially replace Portland cement, which usually results in a lower early strength and longer setting times. Presence of activator(s) can accelerate the break-up of structure and hydration of slags. Many research results have indicated that clinkerless alkali-activated slags even exhibit higher strengths, denser structure and better durability compared with Portland cement. In this paper, the recent achievements in the development of high performance cementing materials based on activated slags such as blast furnace slag, steel slag, copper slag and phosphorus slag are reviewed.

CONCLUSION

1. Use of GGBS as cement replacement increases consistency. Although fineness greatly influenced on proper pozzolanic reaction still GGBS passing 75 micron sieve not giving good strength of mortar. Using GGBS more than 10% in Portland slag cement the strength reducing rapidly.
2. With replacement of cement with RHA the consistency increases. Use of RHA which burned properly in controlled temperature improves the strength of mortar. But use of RHA not giving satisfactory strength result.
3. With the use of superplasticizer it possible to get a mix with low water to cement ratio to get the desired strength.

References

1. Pierre-Claude Aitcin, "Development in the application of high performance concrete", Construction and Building Material, Vol. 9. No. 1, 1995, 13-17
2. Andrzej Ajdukiewicz and Wojciech Radomski, "Trends in the Polish research on high-performance concrete", Cement and Concrete Composite, Vol. 24, 2002, 243-251
3. Pierre-Claude Aitcin, "The durability characteristics of high performance concrete", Cement & Concrete Composite, Vol. 25, 2003, 409-420
4. Moayad N Al-Khalaf and Hana A Yousif, "Use of Rice husk ash in concrete", The International Journal of Cement Composites and Lightweight Concrete, Vol. 6, November 4 1984.
5. Muhammad Soaib Ismail and A. M. Waliuddin, "Effect of rice husk ash on high strength concrete", Construction and Building Material, Vol. 10. No. 7, 1996, 521-526
6. Gemma Rodriguez de Sensale, "Strength development of concrete with rice-husk ash", Cement & Concrete Composite, Vol. 28, 2006,158-160
7. A Oner & S Akyuz, "An experimental study on optimum usage of GGBS for the compressive strength of concrete", Cement & Concrete Composite, Vol. 29, 2007, 505-514.
8. Caijun Shi and Jueshi Qian, "High performance cementing materials from industrial slags", Resources Conservation & Recyclin, Vol. 29, 2000, 195-207
9. K Ganesh Babu and V. Sree Rama Kumar, "Efficiency of GGBS in Concrete", Cement and Concrete Research, Vol. 30, 2000, 1031-1036.