

An Investigation On Optical Characterization of Ag/PVA Nanocomposites

Preeti¹, Dr. Praveen Kumar²

¹Research Scholar, OPJS University, Churu, Rajasthan

²Associate Professor, OPJS University, Churu, Rajasthan

Abstract

Silver- Poly vinyl alcohol Ag/ PVA nanocomposite films were prepared by casting method at room temperature with different amount of AgNO₃ solution (0.001, 0.0015, and 0.002ml). The prepared nanocomposites were characterized using UV–VIS spectrophotometer and the optical properties were investigated in the wavelength range 300-800 nm. The absorption peaks showed a shift towards higher wavelength with increasing AgNO₃ concentration while the energy band gap and absorption edges shifted towards lower energies with the increase of AgNO₃ concentration.

Keywords: Nanocomposite, Silver- Poly Vinyl Alcohol, Thin Films.

1. INTRODUCTION

Polymer-based metal nanoparticles have attracted much attention due to their possibility to combine the features of organic and inorganic materials and because the highly application range offered by these hybrid composites [1-4]. Polymer matrix has the ability to prevent both oxidation and coalescence of nanoparticles and provide long time stability [3-5]. Moreover, incorporation of metal into the polymer matrix improves the thermal stability, mechanical and electrical properties. Metal-polymer nanocomposites and especially silver PVA nanocomposites are interesting functional materials in a lot of fields due to their specific physical, mechanical and antimicrobial properties. [1-5]. PVA as the host polymer for Ag nanoparticles is advantageous due to the reducing ability of the secondary alcohol groups, its excellent film forming properties and optical transparency. There are various techniques for the synthesis of silver nanocomposites, e.g., chemical reduction, laser ablation, gamma radiation, sol-gel method, electron irradiation and photochemical methods [8]. Gautam and Ram prepared Ag/PVA nanocomposites by reduction method [1]. X-ray diffraction, UVVIS analysis, scanning electron microscopy, transmission electron microscopy and current voltage measurements were used to characterize these films. The X-ray diffraction analysis showed that silver metal is present in faced cubic center (fcc) crystal structure. The UV–VIS spectrum revealed a single peak at 433 nm. These results indicate that silver nanoparticles are embedded in PVA [1]. Ghanipour and Dorrnian prepared Ag/PVA films by laser ablation method with different concentration of Ag nanoparticles and studied the effect of different Ag nanoparticles concentrations on the structural and optical properties of Ag/PVA nanocomposite thin films using X-ray diffraction and UV–VIS spectroscopy. Results showed remarkable enhancement in crystallinity of the films by adding silver nanoparticles to PVA. Optical energy band gaps of the samples are decreased with increasing the concentrations of silver nanoparticles [3]. Yunus et al. prepared silver/PVA nanocomposite by using quick precipitation method and using hydrazine as a reduction agent. The samples were characterized by (XRD), (UV-VIS), (TEM) and Z-scan technique were carried out to characterize nonlinear optical properties. The UV-VIS results showed that the prepared nanocomposites show surface plasmon resonance in wavelength range 400-430 nm and it goes to higher wavelength by increasing the amount of reduction agent [9].

2. MATERIALS AND METHODS

AgNO₃ and PVA are used without further purification. AgNO₃ solution of 1 mol/L was first prepared by dissolving AgNO₃ powder in distilled water. The mixture is stirred at room temperature. PVA solution is prepared by dissolving 3g in 100 ml of distilled water, the mixture was magnetically stirred at (60-70) C° for 3 hrs. To each 10 ml of PVA solution, different amount (0.001, 0.0015, and 0.002) ml of AgNO₃ solution was add while keeping

temperature, annealing time and PVA weight % constant. The specimens are labeled as S1, S2 and S3. The heating along with stirring was continued until a brown viscous solution was obtained. The color change indicates the formation of PVA stabilized silver colloid. The reduction of silver ions from silver nitrate by the hydroxy groups of PVA polymer results in the formation of PVA capped silver nanoparticles. Then the solutions were casted on a petri dish and left for (3) days at room temperature to solidify. The films thicknesses were about 60 μm . The thicknesses of films were controlled by casting the same amount of materials onto the same glass Pitri dish size.

The optical constants of Ag/ PVA nanocomposites were calculated by using SPUV-26 UV-VIS double beam spectrophotometer in the wavelength range 300-800 nm. Optical constants such as refractive index (n), extinction coefficient (k), dielectric constants (ϵ) were determined by using the fundamental relations of absorbance (A), transmittance (T) and reflectance (R) respectively. The reflection (R) can be calculated from the values of absorbance and transmission [10]

$$R = 1 - A - T \dots\dots\dots (1)$$

The optical absorption coefficient α can be represented by Lambert-Beer law [11]:

$$\alpha = 2.303 A/t \dots\dots\dots (2)$$

where A: is the absorbance and t: is the sample thickness in (cm). The optical band gap can be determined by Tauc's plot [7, 11], using frequency dependent absorption coefficient that given by:

$$\alpha h\nu = B(h\nu - E_{op})^n \dots\dots\dots (3)$$

α is the absorption coefficient, B is the parameter that depends on the inter band transition probability, $h\nu$ is the incident photon energy, E_g is the optical band gap and (n) is an index characterizing the nature of the electronic transitions causing the optical absorption. (n) can take values 1/2, 3/2, 2, and 3 for direct allowed, direct forbidden, indirect allowed and indirect forbidden transitions, respectively

3. RESULTS AND DISCUSSION

The variation of absorbance (A) and transmittance (T) as a function of wavelength of pure PVA and Ag/ PVA nanocomposites at different concentrations are shown in Fig.(1). and Fig.(2). It can be seen from Fig. (1), the pure PVA sample has a nearly zero absorbance in the visible region because it is a colorless polymer and show no bands in the range of measurement [3,19], it is also found that the absorption of all prepared nanocomposites thin films increase with the increase of AgNO_3 concentration which indicate that higher concentration generate higher number of Ag nanoparticles. The absorption peak above 400nm indicates the formation of silver nanoparticles [1,15]. As the concentration increases there is not only increase in the absorption peak spectra but a red shift in the surface plasmon resonance (SPR) wavelength. This behavior is due to strong interaction of the silver nanoparticles with light that occurs when the conduction electrons on the metal surface undergo collective oscillation. Moreover SPR wavelength can be tuned by changing the particle size and the local refractive index.




Fig.1: Absorption spectra as a function of wavelength for pure PVA and Ag/PVA nanocomposites at different concentrations

The transmittance of pure and Ag/PVA nanocomposites films in the wavelength range 300-800 nm are shown in Fig.(2). It is clear that the transmittance spectra increases with increasing of wavelength. When the concentration of (AgNO_3) increases the transmittance decreased for a lower wavelength range. This is due to the fact that there is some absorption in that wavelength range.




Fig.2: Transmittance spectra as a function of wavelength for pure PVA and Ag/PVA nanocomposites at different concentrations

Fig.(3). a and b show the optical absorption coefficients for pure PVA and Ag / PVA nanocomposites films versus photon energies. The presence of metal nanoparticles in the polymer films could be followed by monitoring the plasmon absorption peaks in the absorption spectrum [1,9]. The larger absorption peak appeared in UV range is due to the energy gap of the PVA polymer which decreases owing to increasing the concentration of Ag nanoparticles in the structure of the films. The position of the absorption edge was determined by extrapolating the linear part of (α) versus ($h\nu$) curves to zero absorption value. The band edge showed a decrease with increasing concentration of Ag nanoparticles in PVA matrix. The absorption edge shifts towards higher wavelength, indicating the decrease in the optical band gap for the doped films. Shift of the absorption edge in the UV regions due to changes in the electron hole in the conduction and valence bands.




Fig.3: Absorption coefficient α spectra as a function of photon energy for pure PVA (a) and Ag/PVA nanocomposites at with different concentrations (b).




Fig.4: Optical band gap spectra as a function of photon energy for pure PVA (a) and Ag/PVA nanocomposites at different concentrations (b)

Fig.(4) a and b show the variation of energy gap for pure PVA and Ag/PVA nanocomposites films, it can be seen that the values of energy gap decrease with increasing AgNO_3 concentration. This decrease due to creation of new levels in the band gap, lead to facilitate the transition of electrons from the valence band to these local levels to the conduction band, consequently the conductivity increases and the band gap decreases [11, 21]. Table (1) summarizes the values of optical band gaps and absorption edges for pure PVA and Ag/PVA nanocomposites films.

Table 1 Optical band gaps and absorption edge for pure PVA and Ag/PVA nanocomposites at different concentrations

Sample	Concentration of (AgNO_3) (ml)	Optical band gap (eV)	
		Direct allowed energy band gap	Absorption edge (eV)
Pure PVA	0	3.60	3.58
S1	0.001	2.4	2.2
S2	0.0015	1.9	1.5
S3	0.002	1.6	1.2

The values of n and k were determined from the measured transmittance and reflectance in the wavelength range 300-800 nm. Evaluation of optical constant is considerably important for the applications in the photonic devices, such as switches, filters and optical waveguides. The refractive index n of prepared films shows anomalous dispersion in the spectral range and normal dispersion in spectral range. This anomalous behavior is due to

resonance effect between the incident light and the electron's polarization, which leads to the coupling of electrons in the Ag/PVA nanocomposites to the oscillation electromagnetic field. An increase in refractive indices values can be observed with the increase of doping concentrations.

4. CONCLUSION

Ag-PVA nanocomposites with different (AgNO_3) concentrations were prepared by casting technique with thickness (60) μm . The UV-VIS spectra of the prepared nanocomposites shows that the optical conductivity increased with the increasing of (AgNO_3) concentration and the presence of absorption peaks above (400) nm indicating the formation of silver nanoparticles. Both of Optical absorption edge and optical energy gap decrease with the increasing of (AgNO_3) concentration.

5. REFERENCES

- [1] Gautam A, Ram S. "Preparation and thermomechanical properties of Ag-PVA nanocomposite films" journal of Materials chemistry and physics, 119, 266-271, 2010.
- [2] Clémenson S., P., Al-couffe, David L., Espuche E. "Structure and morphology of membranes prepared from polyvinyl alcohol and silver nitrate: influence of the annealing treatment and of the film thickness" journal of Desalination, 200, 437–439, 2006.
- [3] Ghanipour M. and Dorrani D. "Effect of Ag-Nanoparticles Doped in Polyvinyl Alcohol on the Structural and Optical Properties of PVA Films" Journal of Nanomaterials Vol.2013, Article ID 897043, 10 pages.
- [4] Ananth N., S., Umapathy J. Sophia, Mathavan T., Mangalaraj D. "On the optical and thermal properties of in situ/ex situ reduced Ag NP's/PVA composites and its role as a simple SPR-based protein sensor" Appl. Nanosci., 1, 87–96, 2011.
- [5] Rong Zeng, Min Zhi Rong, Ming Qiu Zhang, Hai Chun Liang, Han Min Zeng, "Laser ablation of polymer-based silver nanocomposites" Applied Surface Science 187, 239–247, 2002.
- [6] Maribel G, Jean Dille, Stephan Godet "Synthesis of Silver nanoparticles by chemical reduction method and their antibacterial activity", International Journal of chemical and Biomolecular Engineering, 2(3), 2009.
- [7] Kensuke A., Shodo Takei, Minoru M., Akihiko K., Shigehito D., Shinji T., Minoru Fujii, Shinji Hayashi, Keiichi Yamamoto "Preparation and characterization of polymer thin films containing silver and silver sulfide nanoparticles", Thin Solid Films 359, 55-60, 2000.
- [8] Irvani S., Korbekandi H., Mirmohammadi S.V., and Zolfaghari B. "Synthesis of silver nanoparticles: chemical, physical and biological methods", Res Pharm Sci., 9(6): 385–406, 2014.
- [9] Yunus W., Kharazmi A., Saion E., Shahmiri M., Tamchek N., "Synthesis, Characterization and nonlinear Optical properties of Silver/ PVA nanocomposites", Journal Europ. Opt. Soc. Rap.Public. 7, 12040, 2012.
- [10] Aseel S. Jasim, "Preparation and Optical Characterization of Polymer Composites Reinforced by Natural Materials" Journal of Al-Nahrain University, 19 (1), 91-97, March, 2016.
- [11] Mansour A.F., Mansour S.F. and Abdo M.A., "Improvement structural and optical properties of ZnO/ PVA Nanocomposites", journal of Applied physics (IOSR), 7, 60- 69, 2015.
- [12] Ibrahim R. Agool, Ahmed H., "preparation of (PVA-PEG-PVP-MgO, CoO) Nanocomposites and study their optical properties", International Journal of science and Research(IJSR), 2319-7064, 2012.
- [13] Farag A.M., Yahia I.S., Yakuphanoglu F., Kandaz M., Farooq W.A. "Optical properties and the dispersion parameters of new zinc Phthalocyaninebenzofuran derivative prepared by non-vacuum spin coating technique, Optics Communications, 3122-3127, 2012.
- [14] Shehap A.M., Dana S. Akil, "Structural and optical properties of TiO₂ nanoparticles/PVA for different composites thin films "Int. J. Nanoelectronics and Materials 9, 17-36, 2016.
- [15] Sami S. Chiad, Saad F. Oboudi, Khalid H. Abaas, Nadir F. Habubi "characterization of Silver/Poly (Vinyl Alcohol)(Ag/PVA) Films prepared by casting Technique", Iraqi J. of polymers, 16(2), 10-18, 2012.