Optimization of surface grinding process parameter for AISI 321 by Using Taguchi Method

Avinash S. Jejurkar¹, Vijay L. Kadlag²

¹Lecturer, Department of Mechanical Engineering, SVIT, Chincholi, Nashik, Maharashtra, India ²Associate Professor, Department of Mechanical Engineering, SVIT, Chincholi, Nashik, Maharashtra, India

ABSTRACT

Recently stainless-steel AISI-321 finding several applications like Automotive, Aerospace, Nuclear, Chemical plants. The present work takes the subsequent input processes parameters specifically Work speed, feed rate and depth of cut. The objective of this work is to predict the grinding behavior and come through best in operation processes parameters. A software system package is also utilized that integrates these numerous models to simulate what happens throughout surface grinding processes. Predictions from this work are additional analyzed by standardization with actual knowledge. It involves several variables like depth of cut, work speed and feed rate. The aim of any machining method is to maximize the Metal Removal Rate (MRR). In present work to optimize these values Taguchi methodology, ANOVA is employed.

Keyword: - Austenitic stainless steel, surface grinding, Taguchi, S/N ratio ANOVA, Optimization

1. INTRODUCTION

The manufacturing process of surface grinding has been established in the production of slim and flat symmetrical components. Due to the complicated set-up, which results from the big sensitivity of this grinding method to a multiplicity of geometrical, kinematical and dynamical influence parameters, surface grinding is rarely applied inside limited-lot production. The substantial characteristics of this grinding process square measure the synchronic steering and machining of the work piece on its edge. Surface grinding is an essential method for final machining of elements requiring sleek surfaces and precise tolerances. As compared with other machining processes, grinding is costly operation that ought to be used underneath optimum conditions. Although wide used in business, grinding remains perhaps the least understood of all machining processes. The major operating input parameters that influence the output responses, metal removal rate, surface roughness, surface damage, and tool wear etc., are: (i) wheel parameters: abrasives, grain size, grade, structure, binder, shape and dimension, etc., (ii) Work piece parameters: fracture mode, mechanical properties and chemical composition, etc., (iii) Process parameters: work speed, depth of cut, feed rate, dressing condition, etc., (iv) machine parameters: static and dynamic Characteristics, spindle system, and table system, etc.

The proposed work takes the following input processes parameters specifically work speed, feed rate and depth of cut. Alloy 321 is commonly wont to rigid flanges; this application needs precise surface roughness thanks to use in chemical handling pipelines or equipment's. Due to this reason surface grinding for this application require to be ptimum. Henceforthis workthis application is underneath thought. Asoftwarepackage might be used that integrates these numerous models to simulate what happens throughout surface grinding processes. Predictions from this work will be any analyzed by standardization with actual information. It involves several variables such as depth of cut, work speed, feed rate, etc. The main objective in any machining process is to maximize the Metal Removal Rate (MRR). In order to optimize these values Taguchi method, ANOVA and regression analysis is employed.

2. LITERATURE REVIEW

Kamaldeep Singh, Dr. Beant Singh, Mandeep Kumar (2015) states that, Grinding is a very important technique in which material is removed at a high rate with high level of surface finish. In their research work Taguchi method is applied to find optimum process parameters for abrasive assisted surface grinding of AISI D3 tool steel. Experiments are conducted on horizontal spindle reciprocating table surface grinding machine with L18 orthogonal array with input machining variables as type of wheel, depth of cut, table speed, grain size and slurry concentration. After conducting the experiments, MRR is calculated and surface roughness is measured using surface roughness tester. Results are optimized by S/N ratio and analyzed by ANOVA. This study demonstrates that c-BN grinding wheel is preferred for higher MRR and Al2 O3 grinding wheel for better surface finish. Depth of cut is the most significant factor for both MRR and surface roughness.

Gaurav upadhyay, Ramprasad, Kamal Hassan (2015) proposed that, metal removal rate and surface finish are the important output responses in the production with respect to quantity and quality respectively. The objective of this paper is to arrive at the optimal grinding conditions that will maximize metal removal rate when grinding IS 319 brass. Empirical models were developed using design of experiments by Taguchi L9 Orthogonal Array and the adequacy of the developed model is tested with ANOVA. For Metal Remove Rate (MRR), the depth of cut (µm) was the most influencing factor for IS 319 Brass work material followed by grinding wheel speed and work speed.

K Mekala, J Chandradas (2014) sates that the surface grinding parameters on Austenitic stainless steel are conducted using Taguchi design of experiments of L9 orthogonal array was selected with 3 levels with 3 factors and output parameters of Metal removal rate are measured. After conducting experiment optimized by S/N ratio and analyzed by ANOVA and predicts Cutting speed is a dominating parameter of surface grinding. The influence parameter of surface roughness is cutting speed and metal removal rate is influenced by Depth of cut. The optimum parameters of surface grinding overcome problem of poor chip breaking and machining distortion.

M. S. Sukumar, P. Venkata Ramaiah, A. Nagarjuna (2014) worked on Al 6061 material, according to Taguchi orthogonal array (L16) for various combinations of controllable parameters viz. speed, feed and depth of cut. The surface roughness (Ra) is measured and recorded for each experimental run and analyzed using Taguchi S/N ratios and the optimum controllable parameter combination is identified. An Artificial neural network (ANN) model has been developed and trained with full factorial design experimental data and a combination of control parameters have been found from ANN for the surface roughness (Ra) value, obtained from confirmation test, for the optimum control parameters which are obtained from Taguchi S/N ratios analysis. Taguchi method and ANN found different sets of optimal combinations but the confirmation test revealed that both got almost same Ra values. Among the consider parameters, speed has the most influence on the surface finish of the work-piece. The trained ANN is able to predict the Ra values with reasonable accuracy. Taguchi S/N ratio analysis and ANN are useful to find the optimum combination of parameters for getting a good surface finish.

M. Aravind, Dr. S. Periyasamy (2014) states that, the surface grinding process parameters can be optimized by using Taguchi method and Response Surface Methodology (RSM). The process parameters considered in this study are grinding wheel abrasive grain size, depth of cut and feed. An AISI 1035 steel square rod of 100 mm x 10 mm x 10 mm was considered for grinding. The output response was selected as Surface roughness (Ra and Rz). In Taguchi method, L27 orthogonal array was selected and S/N ratios were analyzed to study the surface roughness characteristics. In response surface methodology, Box-Behnken method was used for optimization. Thirteen experiments were conducted in the surface grinding machine. The surface roughness values were entered in the Design Expert software and the optimal solution was obtained. Both methods showed that wheel grain size and depth of cut influences the surface roughness a lot. Feed of the surface grinding has a very minimal effect on the surface roughness value. This study showed that when the input parameters can be varied within the selected levels, Response surface methodology has an edge over Taguchi method. The confirmation experiments were conducted both for the optimal solution obtained from Taguchi and Response surface methodology.

Pawan Kumar, Anish Kumar, Balinder Singh (2013) states that, surface quality and metal removal rate are the two important performance characteristics to be considered in the grinding process. The main purpose of this work is to study the effects of abrasive tools on EN24 steel surface by using three parameters (Grinding wheel speed, table speed & Depth of cut). This study was conducted by using surface grinding machine. In this work, empirical models were developed for surface roughness and metal removal rate by considering wheel speed, table speed and depth of cut as control factors using response surface methodology. In this Response surface methodology (RSM) was applied to determine the optimum machining parameters leading to minimum surface roughness and maximum metal removal rate in Surface grinding process. Surface roughness and material removal rate is strongly dependent on wheel speed, table speed and depth of cut.

Reddy Sreenivasulu (2013) worked on, the influence of cutting speed, feed rate and depth of cut on the

delamination damage and surface roughness on Glass Fiber Reinforced Polymeric composite material (GFRP) during end milling. Taguchi design method is employed to investigate the machining characteristics of GFRP. From the results of ANOVA, it is concluded that cutting speed and depth of cut are the most significant factors affecting the responses, their contribution in an order of 26.84% and 40.44% respectively. Confirmatory experiments show that $5.052\mu m$ for surface roughness and 1.682 delamination damage to validate the used approach after conducting with optimal setting of process parameters. Finally, artificial neural network has been applied to compare the predicted values with the experimental values, the deviations are found in the range of 3.7%, it shows good agreement between the predictive model results and the experimental measurements .

Mustafa Kemal Kulekcy (2013) states that, the Taguchi method that is a powerful tool to design optimization for quality can be used to find the optimum surface roughness in grinding operations. An orthogonal array, a signal-to-noise (S/N) ratio, and an analysis of variance (ANOVA) are employed to investigate the surface-roughness characteristics of AISI 1040 steel plates using EKR46K grinding wheels. Through this study, not only the optimum surface roughness for grinding operations be obtained, but the main grinding parameters affecting the performance of grinding operations can also be found. Experimental results are provided to confirm the effectiveness of this approach. The results of this study showed that the depth of cut and the wheel speed have significant effects on the surface roughness, while the rate of feed has a lower effect on it. This study showed that the depth of cut and the wheel speed have significant effects on the surface roughness. The rate of feed has a lower effect on the surface roughness.

3. PROBLEM IDENTIFICATION

Alloy 321 is commonly used to handle sulfur, pulp liquor, acid dyestuffs, acetylating and nitrating mixtures, bleaching solutions, severe oil and coal, and most of the chemical compounds. Some core applications that use alloy 321 include:

- Rigid Flanges
- Pipes
- Butt weld fittings
- Fasteners
- Chemical and petrochemical processing equipment
- Condensers in fossil and nuclear fueled power generation plants
- Food processing equipment
- Textile equipment.

The identification of machining and grinding difficulties for Austenitic stainless steel (AISI 321) which cannot be tackled using conventional technique because of following problems occur in Grinding.

- Poor Chip Breaking.
- High Work hardened.
- Tendency to sticky.
- Transformation Induced plasticity.
- Passive surface is affected.
- Machining distortion

The above problems are to overcome during surface grinding and achieve good surface finish and close dimensional accuracy.

4. METHODOLOGY

The Taguchi method can be used for this work. Small arrays can be drawn out manually; large arrays can be derived from deterministic algorithms. Arrays can be found online. The arrays are selected by the number of parameters (variables) and the number of levels. This is further explained later in this article. Analysis of variance on the collected information from the Taguchi design of experiments can be used to select new parameter values to optimize the performance characteristic. Data from the arrays can be analyzed by plotting the data and performing a visual analysis, ANOVA.

4.1. Taguchi Method of Orthogonal Arrays

Parameters-3

- 1. Rotational speed- e.g. A, B, C
- 2. Feed (Table speed) e.g. P, Q, R
- 3. Depth of cut-e.g. L, M, N

Here there are total three levels for each parameter.

Therefore refer Taguchi table of orthogonal arrays L9.

Table 1: Layout of experimental design according to L9 array

Experi ment	Rotational speed	Feed	Depth of cut
	A STATE OF THE PARTY OF THE PAR		lo.
1	A	P	L
2	A	Q	M
3	A	R	N
4	В	P	L
5	В	Q	M
6	В	R	N
7	С	P	L
8	C	Q	M
9	С	R	N

Table 2: Process Parameters with their values at corresponding levels.

Sr.	Process	Dongo	Level	Level	Level
No	Parameters	Range	<u> </u>	2	3
	Rotational	400- 1100	400	750	1100
Î	1 speed	m/min	400	730	1100
		3-15	No.		
2	Feed		3	9	15
2		m/min			
	Depth of	3-18	3	10.5	18
3	cut	μm			

5. RESULTS AND DISCUSSION

Table 3: Result	table for material	removal rate	(MRR)

Sr. No.	Speed (rpm)	Feed (m/min)	DOC (µm)	MRR (gm/min)
1	400	3	3	9.1
2	400	9	10.5	11.0
3	400	15	18	13.7
4	750	3	10.5	13.8
5	750	9	18	14.2
6	750	15	3	12.9
7	1100	3	18	13.4
8	1100	9	3	14.1
9	1100	15	10.5	14.9




Chart 1: Main Effect plot (data means) for SN Ratios

After conducting the experiment on surface grinding of austenitic stainless (AISI 321) for material removal rate are given below.

- Speed is a dominating parameter of Surface grinding for material removal rate.
- The optimum parameter for material removal rate for surface grinding of Austenitic stainless steel AISI 321is 1100 rpm of speed, 15 m/min of Feed and 10.5 µm depth of cut are shown in Table 3.
- However Austenitic stainless steel (AISI 321) is having good machinability characteristic and Produce excellent surface finish.
- Austenitic stainless steel produce good surface finish and get minimum crack tendency.

6. CONCLUSION

After conducting experiments on surface grinding, I conclude the following:

- Austenitic stainless steel produces good surface finish during surface grinding process in optimum grinding parameters.
- Close tolerance can be achieved during surface grinding.
- Speed play an important role in surface grinding and produce maximum material removal rate in AISI 321 austenitic stainless steel were 1100 rpm of cutting speed 15 m/min and 10.5 μ m of depth of cut.
- Austenitic stainless (AISI 321) Provide good machinability property.
- The influence parameter of material removal rate is speed.
- The optimum parameters of surface grinding overcome problem of poor chip breaking and machining distortion

7. REFERENCES

- [1]. Mustafa Kemal Külekcý., Analysis of process parameters for a surface-grinding process based on the taguchi method, 2013., SSN 1580-2949 MTAEC9, 47(1)105
- [2]. Gaurav Upadhyay, Ramprasad, Kamal Hassan., Optimization of Metal Removal Rateon Surface Grinding For Is 319 Brass Using Taguchi Method, Vol. 5, Issue 6, (Part -3) June 2015, pp.63-67.
- [3]. K Mekala1,J Chandradas. "Optimization of Surface Grinding Parameters Of Austenitic Stainless Steel Rods (Aisi 316) By Taguchi Method". IJMERR 2014.
- [4]. M.S. Sukumar, P. Venkata Ramaiah. A. Nagarjuna, Optimization and Prediction of Parameters in Face Milling of Al-6061 Using Taguchi and ANN Approach, GCMM 2014.
- [5]. M.Aravind, Dr.S.Periyasamy. Optimization of Surface Grinding Process Parameters By Taguchi Method And Response Surface Methodology, IJERT Vol. 3 Issue 5, May 2014.
- [6].Pawan Kumar, Anish Kumar, Balinder Singh., Optimization of Process Parameters in Surface Grinding Using Response Surface Methodology., 2013 IJRMET Vol. 3.
- [7].Reddy Sreenivasulu.,Optimization of Surface Roughness and Delamination Damage of GFRP Composite Material in End Milling using Taguchi Design Method and Artificial Neural Network., 2013,IConDM.
- [8]. Kamaldeep Singh, Dr. Beant Singh, "Experimental Investigation of Machining Characteristics of AISI D3 Steel with Abrasive Assisted Surface Grinding". IRJET, 2015 Volume: 02 Issue: 04.

