

A LITERATURE REVIEW ON STUDY OF COLLOIDAL NANO-SILICA AS PARTIAL REPLACEMENT OF CEMENT IN CONCRETE

Deepak Ranjan¹, Prof. Rahul Sharma²

¹Research Scholar

²Asst. Professor

Department of Civil Engineering
Prashanti Institute Of Science and Technology, Ujjain(M.P.)

ABSTRACT

In the recent year, there has been various attempts for improving the properties of concrete with respect to strength and durability point of view, especially in adverse environments. High performance concrete appears to be better choice for a strong as well as durable structure. A large amount of by-product or wastes such as fly-ash, copper slag, silica fume etc. are generated by industries, which causes environmental as well as health problems due to dumping and disposal. Proper introduction of Colloidal Nano silica in concrete improves both the mechanical and durability characteristics of the concrete. This paper present literature review on replacement of Cement by Colloidal Nano silica which includes current and future trends of research.

Keywords: Colloidal Nano-Silica Liquid (NS), Compressive strength (CS), Cement, Strength

1. INTRODUCTION

Leaving the waste materials to the climate straightforwardly can cause natural issue. Consequently the reuse of waste material from Industries has been underlined. Waste can be utilized to create new items or can be utilized as admixtures with the goal that characteristic assets are utilized all the more proficiently and the climate is shielded from squander. These modern squanders are unloaded in the close by land and the characteristic richness of the dirt is ruined.

Nano-SiO₂ has been found to improve concrete workability and strength, to increase resistance to water penetration, and to help control the leaching of calcium, which is closely associated with various types of concrete degradation. Nano-SiO₂ was found to be more efficient in enhancing strength than silica fume. The raw material of polypropylene is derived from monomeric C₃H₆ which is purely hydrocarbon.

2. REVIEWS OF ARTICLES

- **M.S.J. Hasmi and A.L.Hussain (2021)** studied that the improvement of mechanical properties and the occurrence of the pozzolanic reaction after 28 days of hydration.
- **Dr. A. Thirumurugan(2020)** studied thatt the compressive strength of cubes increases upto 3% replacing of cement with nanosilica
- **Chenglong Zhuang and Yu Chen(2019)** Studied When nano-SiO₂ is used to replace part of the cement, the high activity of nano-SiO₂ helps to promote the hydration reaction of concrete, which shortens the setting time of nano-SiO₂.
- **N.Mohanraj, E.Arundhava Priya, A.Gopalan(2019)** This paper studies that the mechanical properties of the hybrid concrete were carried out. The present study aims at producing the concrete specimen by reinforcing constant level of fibers (steel fibers of 0.7%, and polypropylene fibers of 0.3%) with the different percentage (5%, 10%, 15% and 20%) of silica fume and then comparing it with normal and fiber reinforced concrete. Different tests were carried out on the hybrid concrete specimen like compressive strength test, flexural strength test, and durability tests on normal concrete, the hybrid concrete exhibits series of crevice while loading and also has higher flexural and compressive

strength than the normal concrete.

- **Swapnil Gupta(2018)** studied the Effect of colloidal nano silica and polypropylene fiber on the strength and durability characteristics of M40 concrete. The main parameter investigated in this study is M40 grade concrete with partial replacement of cement by colloidal nano silica by 0%, 5%, 10% and polypropylene fiber by 0%, 0.5% and 1.0% a detailed experimental study in Compressive strength, flexural strength at age of 7, 14 and 28 days was carried out. Results Shows that colloidal nano silica and polypropylene fiber in concrete has improved the performance of concrete in strength as well as durability aspect.
- **Akash Kumar, Gurpreet Singh(2018)** has investigated that From the compressive strength results, it can be observed that increase in compressive strength of cement mortar is observed on addition of a certain minimum quantity of Nano-Silica. The increase in strength is maximum for Nano silica 5% by weight of cement.
- **Reddy A.N, Meena T(2018)** Ternary Blended Concrete (TBC) with Nano-Silica (NS) is receiving special attention because of its ability to improve the performance of concrete as compared with the control concrete. The present investigation deals about the behavior of TBC produced, using Fly Ash (FA) and Alccofine (ALC) as a partial replacement for cement along with four different types of colloidal NS (CemSynXLP, CemSynXTX, CemSynXFX, CemSynXTXla) as additives. The compressive strength of M30 grade of TBC was tested after 7, 14 and 28 days of curing. From the study, it has been found that the TBC mix with 25% replacement for cement (FA at 15% and ALC at 10%) and with addition of 1% CemSynXTXla type of NS as an additive has achieved higher strength than all other types of TBC mixes.
- **Irfaz ur Rahman Najar, Jagdish Chand kambooj (2018)** has investigated that fiber addition On the basis of existing review of literature it can be concluded that the strength increases in concrete with increases in silica fume rate upto 15% after that it gets decreased, but by adding steel fibre upto 2% the strength gets increased upto 10%-15%. On other side when fly ash is added to the plain concrete, it has been noted that the higher the percentage of F.A the higher the values of compressive strength until 30% of F.A, after that the increase in the percentage of F.A lead to decrease in values of concrete compressive strength. Overall the best results are shown at the percentage of 15%-20% of adding silica fume and fly-ash.
- **Rahul Dogra, Ankit (2016)** has investigated on concrete mix design of M25 grade by adding various types of admixtures and get more strength as well as it's become economical mix design as far as cost is concern. They observed that more strength than require strength in M25 grade so they reduced the grade like M15 and get the target strength. They took target strength 30. Thus for target strength 30 they can use this type of mix design by adding various types of admixtures in grade of M15 and mix design became economical. Compressive strength of steel and glass fiber at 28 days is 49.84 N/mm² and 25.72 N/mm² respectively. The scope of present research accord with the strength properties of concrete, on the effect of fractionally substitution of cement by silica fume with different percentages viz 0%, 5%, 7.5 and 10% was used in the concrete and polypropylene fiber used with percentage 0%, 0.5%. Strength Properties studies involve compressive strength flexural strength tensile strength and abrasion. In present research the strength properties of high strength concrete of M30 grade at 7 days 14 days 28 days characteristic strength with different replacing levels of cement with silica fume are consideration. Standard cubes 15cm x 15cm x 15cm, standard cylinders 15cm dia x 30cm height and standard beam 10cm x 10cm x 50cm were considered in the research. The study bring that the use of waste material like silica fume develop the strength properties of concrete, which is otherwise unsafe to the environment and thus may be used as a fractionally replacement of cement. The partial replacement of 10% silica fume with cement can giving most extreme conceivable compressive strength with polypropylene fiber. Addition of polypropylene fiber improves the tension stiffening effect considerably and this increase the bond stress of reinforced bars in composite fiber reinforced concrete than in plane concrete. Silica fume has no large impact on flexural strength of concrete. In this perspective tests results exhibited in this study, it is fulfilled that a mixed design through 10% silica fume and 0.05% fiber volume division was ideal in flexural quality by means of keeping up an attractive workability. Workability and flow characteristics are reduce by adding of polypropylene fibers in concrete mix; and it also diminishes segregation and bleeding in the concrete blends. The early age shrinkage of polypropylene fibers decrease and dampness loss of the concrete blend not withstanding when low volume divisions of polypropylene fiber are used. The deformation limit of concrete improve by addition of polypropylene fibers (PPF) and also upgrades the material ductility of concrete. Polypropylene fibers reduce the settlement, plastic, water permeability and shrinkage.
- **D.Prasanya, S.Vignesh, R.Gurulakshmi, B.Boomapriya (2016)** studied that silica fume(SF) is used as a partial replacement of cement and polypropylene fiber (PP) is added in order to investigate the mechanical properties of concrete. Silica fume were partially replaced from 5% to 25% and 0.1% of polypropylene fiber were added to test for its compressive and tensile strength. The result of 7th and 28th days of concrete were compared with those of conventional concrete, reveals that silica fume in combination with polypropylene fiber yields high strength both in compression and

in tension. The addition of polypropylene fiber increases the strength of concrete by reducing its unit weight whereas the silica fume act as a better replacing material with its own characteristics. It is observed that the optimum percentage for replacement of Silica fume is 10% and addition of 0.1% Polypropylene fiber increases the compressive and tensile strength up to 27.18N/mm² and 4.4N/mm² respectively.

3. CONCLUSION

The review of earlier studies related to partial replacement of Cement with Colloidal Nano Silica reveals that there is a significant change in the strength properties of concrete such as compressive strength, flexural strength,. These experiments were carried out in various grade concrete to find out the result. From the above literature reviews optimum percentage of colloidal Nano Silica varies from 5% to 15% Up to these Percentage Replacement improvement in the strength of concrete has been observed in terms of Compressive Strength, Flexural Strength and Tensile Strength on partial replacement of Cement with colloidal Nano Silica. Previous studied also shows that colloidal Nano Silica, Silica Fume concretes possess superior durability properties

REFERENCES

1. Dr. A. Thirumurugan(2020) EXPERIMENTAL INVESTIGATION OF HYBRID FIBER CONCRETE WITH NANOSILICA International Journal of Scientific & Engineering Research Volume 11, Issue 3, March-2020 ISSN 2229-5518
2. Chenglong Zhuang and Yu Chen(2019) The effect of nano-SiO₂ on concrete properties: a review <https://www.degruyter.com/document/doi/10.1515/ntrev-2019-0050/html>
3. N.Mohanraj, E.Arundhava Priya, A.Gopalan(2019) International Journal of Innovative Technology and Exploring Engineering (IJITEE) ISSN: 2278-3075, Volume8 Issue-6S, April 2019 “Experimental Study on Hybrid Concrete Using Steel Fiber Polypropylene Fiber and Silica Fume”
4. Swapnil Gupta(2018) “Assessment-of-influence-on-mechanical-properties-of-m40-grade-of-concrete-by-using-polypropylene-fiber-and-nano-silica-liquid”
5. Akash Kumar, Gurpreet Singh(2018) Effect of Nano Silica on the Fresh and Hardened Properties of Cement Mortar” International Journal of Applied Engineering Research ISSN 0973-4562 Volume 13, Number 13 (2018) pp. 11183-11188
6. Irfaz ur Rahman Najar, Jagdish Chand kambooj (2018), Combione effect of Silica fume, Fly ash and steel fiber on reinforced concrete
7. EFFECT OF SILICA FUME ON VARIOUS PROPERTIES OF FIBRE REINFORCED CONCRETE by Rahul Dogra International Journal of Civil Engineering and Technology (IJCIET) Volume 7, Issue 4, July-August 2016.
8. D.Prasanya, S.Vignesh, R.Gurulakshmi, B.Boomapiya (2016) Ajay, V., Chandak, R., and Yadav, R.K., . “Effect of micro silica on the strength of concrete with ordinary Portland cement” Research journal of Engineering Science ISSN 2278-9472 vol.1 (3),